

Natural Stone Product Data Sheet



Type of Stone	ASTM C97 Absorption (Max)	Mohs Hardness	ASTM C241 Abrasive Resistance	ASTM C170 Compressive Strength (Min)
Granite	.40%	6-7	25	19,000 psi
Marble	2.5%	3-4	10	5,000 psi
Quartzite	1.00%	7	8	20,000 psi
Onyx (Calcite)	.20%	6-7	10	7,500 psi
Dolomite	.20%	6-7	10	7,500 psi